

PRODUCT: QUIL-NAZZO



Design reference
V16029 - Light Grey

Other references available:
C15167 - Beige; C15953 - Mid
Grey; V16028 - White; V16030 -
Dark Grey; V16031 - Black

SUMMARY

- Slimline high density (2.44 Tonne/M³) pressed anti-slip tile supplied pre-finished with beveled or straight edges
- Excellent choice for high traffic mass transit environments
- Suitable for use on London Underground, Network rail and Airport projects
- Meets HSE recommendations for safe co-efficient of slip resistance
- Typical Pendulum test value (TPTV) of 40+ in wet condition and 62 in dry using a 96 (formerly four 'S') rubber slider. For ramps TPTV of 50+ in wet condition, 66 in dry with textured finish
- 5% Carborundum for slip resistance incorporated to full thickness of tile providing hard wearing, anti-slip properties throughout the life of the product.
- Can be monolithically bedded on cement and sand or fixed in adhesive
- Easy to maintain with neutral detergent and twin tank scrubbing machines fitted with nylon brushes
- Typical design life 35 years plus
- Case hardener (impregnator) factory applied reducing site operations thus speeding up installation
- 400 x 400 x 18 or 20mm, 600 x 600 x 22mm and 600 x 298 x 22mm modules available in a wide range of colours.



TECHNICAL SPECIFICATION

PRODUCT: QUIL-NAZZO		TILE FINISH: Textured Surface Finish
AVAILABLE SIZE (mm)	WEIGHT PER M ²	TYPICAL APPLICATIONS
400 X 400 X 18	45Kg	External Areas, Ramped Areas, Wet Areas, Mass Transit Areas, Public Areas, Shopping Centres, Supermarkets, Airports, Railway Stations, Food Preparation Areas, Public Buildings, Retail and Domestic Areas.
400 X 400 X 20	50Kg	
600 X 600 X 22	55Kg	
600 X 298 X 22	55Kg	

PALLET DETAILS:				
TILE SIZE (mm)	PALLET DIMS (mm)	AREA OF COVERAGE (M ²)	NUMBER OF TILES	APPROX WEIGHT (Kg's)
400 X 400 X 18/20	1130 X 830 X 550	16.64/15.36	104/96	760/780
600 X 600 X 22	1200 X 650 X 750	15.84	44	885
600 X 298 X 22	1200 X 650 X 750	15.84	88	885

TECHNICAL DETAILS:			
CHARACTERISTICS	TEST METHOD	REQUIREMENT	TYPICAL TEST VALUE
LENGTH & WIDTH	BS EN 13748-1: 2004	± 0.3%	Conform
TILE THICKNESS	BS EN 13748-1: 2004	± 2.0mm	Conform
WATER ABSORPTION TO THE FACE OF TILE	BS EN 13748-1: 2004	Not greater than 0.40g/cm ²	0.16 g/cm ²
WATER ABSORPTION TO THE WHOLE TILE	BS EN 13748-1: 2004	Not greater than 8%	4.47%
BREAKING LOAD	BS EN 13748-1: 2004	Not less than 2.5 kN where the tile has a surface area <1100 cm ²	3.08 kN
BREAKING STRENGTH	BS EN 13748-1: 2004	No individual result of the failure stress shall be less than 4.00 Mpa	7.0 Mpa
RESISTANCE TO DEEP ABRASION mm ³	BS EN 13748-1: 2004	No individual test result exceeds 25mm	Less than 25mm – Modified Capon Test
REACTION TO FIRE	N/A	N/A	Class A1, without testing (see decision 96/603/EC, as amended)

ADDITIONAL DETAILS:	
DESCRIPTION	VALUE
Possible to re-grind surface in future	Yes
Typical Pendulum Test Values (PTV's) – 96 Slider	63 to 65 (Dry) / 40 to 45 (Wet)

TECHNICAL SUPPORT:		
Contact: Quiligotti Sales	Telephone: 0161 727 9798	E-mail: sales@quiligotti.co.uk