



SLIP RESISTANT

PRODUCT GROUP: Slip Resistant	TILE FINISH: Textured Surface Finish
--------------------------------------	---

AVAILABLE SIZES	WEIGHT PER M ²	TYPICAL APPLICATIONS
297 x 297 x 28	66kg	External Areas, Ramped Areas, Wet Areas, Mass Transit Areas, Public Areas, Shopping Centres, Supermarkets, Airports, Railway Stations, Food Preparation Areas, Public Buildings, Retail and Domestic Areas.
300 x 300 x 28	66kg	
397 x 397 x 33	78kg	
400 x 400 x 33	44kg	
497 x 497 x 38	84kg	
500 x 500 x 38	84kg	
597 x 597 x 40	119kg	

PALLET DETAILS:

TILE SIZE (MM)	PALLET DIMS (MM)	AREA OF COVERAGE (M ²)	NUMBER OF TILES	APPROX WEIGHT (KG)
297 x 297 x 28	950 x 950 x 800	19.441	216	1300
300 x 300 x 28	950 x 950 x 800	19.441	216	1300
397 x 397 x 33	950 x 950 x 650	9.60	60	760
400 x 400 x 33	950 x 950 x 650	9.60	60	760
497 x 497 x 38	1010 x 1010 x 720	15	60	1400
500 x 500 x 38	1010 x 1010 x 720	15	60	1400
597 x 597 x 40	1210 x 800 x 750	10.60	30	1050

Note: 597 x 597 x 40mm tiles will be delivered on 1200 x 800 Euro Pallets

TECHNICAL DETAILS

CHARACTERISTICS	TEST METHOD	REQUIREMENT	TYPICAL TEST VALUE
LENGTH & WIDTH	BS EN 13748-1: 2004	±0.3%	Conform
TILE THICKNESS	BS EN 13748-1: 2004	Calibrated (slimline) tiles ±1.0mm. Standard Tiles ±2.0mm (for tiles of D39mm and under) ±3.0 mm (for tiles D40mm and over)	Conform
WATER ABSORPTION TO THE FACE OF TILE	BS EN 13748-1: 2004	Not greater than 0.40g/cm ²	0.25 g/cm ²
WATER ABSORPTION TO THE WHOLE TILE	BS EN 13748-1: 2004	Not greater than 8%	5.0% average
BREAKING LOAD	BS EN 13748-1: 2004	Not less than 2.5 kN where the tile has a surface area <1100cm ²	4.75 kN
BREAKING STRENGTH	BS EN 13748-1: 2004	No individual result of the failure stress shall be less than 4.00 Mpa	5.75 Mpa
RESISTANCE TO DEEP ABRASION MM ³	BS EN 13748-1: 2004	No individual test result exceeds 25mm	Less than 25mm – Modified Capon Test
REACTION TO FIRE	N/A	N/A	Class A1, without testing (see Decision 96/603/EC, as amended)

ADDITIONAL DETAILS:

DESCRIPTION	VALUE
Possible to re-grind surface in the future	No
Typical Pendulum Test Values (PTV's) – 96 Slider	65 (Dry) / 38 to 45 (Wet)

TECHNICAL SUPPORT:

Contact: Colin Price	Telephone: 0161 727 9798	Email: colin.price@quiligotti.co.uk
----------------------	--------------------------	-------------------------------------